



PE80 PIPES max allowed tensile strenght during placement at 20 °C

8 MPa

outside diameter mm	Pipe Serie (S)																											
	25		20		16		12,5		10,5		10		8,3		8		6,3		5		4		3,2		2,5		2	
	diameter / wall thickness relationship (SDR)																											
	51		41		33		26		22		21		17,6		17		13,6		11		9		7,4		6		5	
wall thickness mm	strenght kgf	wall thickness mm	strenght kgf	wall thickness mm	strenght kgf	wall thickness mm	strenght kgf	wall thickness mm	strenght kgf	wall thickness mm	strenght kgf	wall thickness mm	strenght kgf	wall thickness mm	strenght kgf	wall thickness mm	strenght kgf	wall thickness mm	strenght kgf	wall thickness mm	strenght kgf	wall thickness mm	strenght kgf	wall thickness mm	strenght kgf	wall thickness mm	strenght kgf	
10																												
12																												
16																												
20																												
25																												
32																												
40																												
50																												
63																												
75	1,8	338	1,9	356	2,3	429	2,9	536	3,5	642	3,6	659	4,3	779	4,5	813	5,6	996	6,8	1189	8,4	1434	10,3	1708	12,5	2002	15,1	2318
90	1,8	407	2,2	495	2,8	626	3,5	776	4,1	903	4,3	945	5,1	1110	5,4	1171	6,7	1430	8,2	1719	10,1	2068	12,3	2449	15,0	2883	18,1	3335
110	2,2	608	2,7	743	3,4	929	4,2	1139	5,0	1346	5,3	1422	6,3	1674	6,6	1749	8,1	2115	10,0	2562	12,3	3079	15,1	3672	18,3	4300	22,1	4977
125	2,5	785	3,1	969	3,9	1210	4,8	1479	5,7	1743	6,0	1830	7,1	2145	7,4	2230	9,2	2730	11,4	3318	14	3982	17,1	4728	20,8	5553	25,1	6425
140	2,8	985	3,5	1224	4,3	1495	5,4	1863	6,4	2191	6,7	2289	8,0	2706	8,3	2801	10,3	3423	12,7	4142	15,7	5000	19,2	5943	23,3	6967	28,1	8056
160	3,2	1286	4,0	1599	4,9	1948	6,2	2443	7,3	2856	7,7	3005	9,1	3519	9,5	3663	11,8	4481	14,6	5439	17,9	6517	21,9	7749	26,6	9091	32,1	10519
180	3,6	1627	4,4	1980	5,5	2459	6,9	3060	8,2	3610	8,6	3777	10,2	4438	10,7	4642	13,3	5681	16,4	6874	20,1	8235	24,6	9794	29,9	11499	36,1	13309
200	3,9	1960	4,9	2450	6,2	3079	7,7	3794	9,1	4451	9,6	4683	11,4	5509	11,9	5735	14,7	6979	18,2	8477	22,4	10193	27,4	12117	33,2	14188	40,1	16428
225	4,4	2487	5,5	3093	6,9	3856	8,6	4768	10,3	5666	10,8	5927	12,8	6959	13,4	7265	16,6	8863	20,5	10741	25,2	12900	30,8	15324	37,4	17976	45,1	20787
250	4,9	3077	6,2	3873	7,7	4780	9,6	5913	11,4	6969	11,9	7260	14,2	8579	14,8	8919	18,4	10918	22,7	13219	27,9	15876	34,2	18909	41,6	22211	50,1	25658
280	5,5	3868	6,9	4828	8,6	5980	10,7	7383	12,8	8763	13,4	9153	15,9	10759	16,6	11202	20,6	13691	25,4	16568	31,3	19944	38,3	23717	46,5	27818	56,2	32224
315	6,2	4906	7,7	6063	9,7	7587	12,1	9390	14,4	11090	15,0	11529	17,9	13625	18,7	14196	23,2	17344	28,6	20986	35,2	25233	43,1	30024	52,3	35200	63,2	40771
355	7	6241	8,7	7719	10,9	9610	13,6	11896	16,2	14062	16,9	14639	20,1	17246	21,1	18050	26,1	21993	32,2	26630	39,7	32069	48,5	38085	59,0	44742		
400	7,9	7936	9,8	9797	12,3	12218	15,3	15080	18,2	17803	19,1	18639	22,7	21943	23,7	22849	29,4	27915	36,3	33824	44,7	40689	54,7	48390	66,5	56819		
450	8,8	9947	11,0	12372	13,8	15422	17,2	19072	20,5	22558	21,5	23603	25,5	27733	26,7	28956	33,1	35354	40,9	42868	50,3	51508	61,5	61213				
500	9,8	12308	12,3	15369	15,3	19000	19,1	23533	22,8	27875	23,9	29152	28,4	34314	29,7	35786	36,8	43671	45,4	52876	55,8	63502	68,3	75540				
560	11	15472	13,7	19175	17,2	23919	21,4	29530	25,5	34919	26,7	36480	31,7	42906	33,2	44808	41,2	54761	50,8	66271	62,5	79661						



Tel.: +32(0)87.59.77.00
Fax: +32(0)87.55.28.93
http://www.eupen.com
e-mail:info@eupen.com

Malmedyer Straße 9 - 4700 EUPEN - BELGIUM
MWSt - TVA - BTW BE 437.768.918/09.26.13
HR - RC - HR Eupen 60 426

Technical data, designs and specifications presented in this file are not binding and are subject to change without prior notice.



PE100 PIPES max allowed tensile strenght during placement at 20 °C

10 MPa

outside diameter mm	Pipe Serie (S)																												
	25		20		16		12,5		10,5		10		8,3		8		6,3		5		4		3,2		2,5		2		
	diameter / wall thickness relationship (SDR)																												
	51		41		33		26		22		21		17,6		17		13,6		11		9		7,4		6		5		
	wall thickness	strenght	wall thickness	strenght	wall thickness	strenght	wall thickness	strenght	wall thickness	strenght	wall thickness	strenght	wall thickness	strenght	wall thickness	strenght	wall thickness	strenght	wall thickness	strenght	wall thickness	strenght	wall thickness	strenght	wall thickness	strenght	wall thickness	strenght	
	mm	kgf	mm	kgf	mm	kgf	mm	kgf	mm	kgf	mm	kgf	mm	kgf	mm	kgf	mm	kgf	mm	kgf	mm	kgf	mm	kgf	mm	kgf	mm	kgf	
10																													
12																													
16																													
20																													
25																													
32																													
40																													
50																													
63																													
75	1,8	422	1,9	445	2,3	536	2,9	670	3,5	802	3,6	824	4,3	974	4,5	1016	5,6	1245	6,8	1486	8,4	1792	10,3	2135	12,5	2502	15,1	2897	
90	1,8	509	2,2	619	2,8	782	3,5	970	4,1	1128	4,3	1181	5,1	1387	5,4	1464	6,7	1788	8,2	2149	10,1	2585	12,3	3061	15,0	3603	18,1	4168	
110	2,2	760	2,7	928	3,4	1161	4,2	1424	5,0	1682	5,3	1778	6,3	2093	6,6	2186	8,1	2644	10,0	3203	12,3	3849	15,1	4590	18,3	5375	22,1	6222	
125	2,5	981	3,1	1211	3,9	1513	4,8	1848	5,7	2178	6,0	2287	7,1	2681	7,4	2787	9,2	3412	11,4	4148	14	4977	17,1	5909	20,8	6941	25,1	8031	
140	2,8	1231	3,5	1530	4,3	1869	5,4	2328	6,4	2739	6,7	2861	8,0	3382	8,3	3501	10,3	4279	12,7	5178	15,7	6250	19,2	7428	23,3	8708	28,1	10070	
160	3,2	1607	4,0	1999	4,9	2434	6,2	3054	7,3	3570	7,7	3756	9,1	4398	9,5	4579	11,8	5601	14,6	6799	17,9	8146	21,9	9686	26,6	11364	32,1	13148	
180	3,6	2034	4,4	2475	5,5	3074	6,9	3825	8,2	4512	8,6	4721	10,2	5547	10,7	5802	13,3	7101	16,4	8593	20,1	10293	24,6	12243	29,9	14373	36,1	16636	
200	3,9	2450	4,9	3062	6,2	3848	7,7	4742	9,1	5564	9,6	5854	11,4	6886	11,9	7169	14,7	8724	18,2	10597	22,4	12741	27,4	15146	33,2	17735	40,1	20535	
225	4,4	3109	5,5	3867	6,9	4820	8,6	5960	10,3	7082	10,8	7409	12,8	8699	13,4	9081	16,6	11079	20,5	13426	25,2	16125	30,8	19155	37,4	22470	45,1	25983	
250	4,9	3847	6,2	4841	7,7	5975	9,6	7391	11,4	8711	11,9	9074	14,2	10723	14,8	11148	18,4	13648	22,7	16524	27,9	19845	34,2	23636	41,6	27764	50,1	32073	
280	5,5	4835	6,9	6035	8,6	7475	10,7	9228	12,8	10953	13,4	11441	15,9	13448	16,6	14003	20,6	17113	25,4	20710	31,3	24929	38,3	29646	46,5	34772	56,2	40279	
315	6,2	6132	7,7	7578	9,7	9484	12,1	11738	14,4	13863	15,0	14411	17,9	17031	18,7	17745	23,2	21680	28,6	26232	35,2	31541	43,1	37530	52,3	43999	63,2	50963	
355	7	7802	8,7	9649	10,9	12012	13,6	14870	16,2	17577	16,9	18299	20,1	21558	21,1	22563	26,1	27491	32,2	33287	39,7	40087	48,5	47606	59,0	55928			
400	7,9	9920	9,8	12246	12,3	15272	15,3	18850	18,2	22253	19,1	23299	22,7	27428	23,7	28561	29,4	34893	36,3	42280	44,7	50861	54,7	60488	66,5	71023			
450	8,8	12434	11,0	15465	13,8	19278	17,2	23840	20,5	28197	21,5	29504	25,5	34666	26,7	36195	33,1	44192	40,9	53584	50,3	64385	61,5	76516					
500	9,8	15385	12,3	19211	15,3	23749	19,1	29416	22,8	34844	23,9	36440	28,4	42892	29,7	44732	36,8	54589	45,4	66095	55,8	79377	68,3	94425					
560	11	19340	13,7	23969	17,2	29899	21,4	36912	25,5	43649	26,7	45600	31,7	53632	33,2	56010	41,2	68451	50,8	82839	62,5	99576							



Tel.: +32(0)87.59.77.00
Fax: +32(0)87.55.28.93
http://www.eupen.com
e-mail: info@eupen.com

Malmedyer Straße 9 - 4700 EUPEN - BELGIUM
MWSt - TVA - BTW BE 437.768.918/09.26.13
HR - RC - HR Eupen 60 426

Technical data, designs and specifications presented in this file are not binding and are subject to change without prior notice.